




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : G02B 6/293, 6/34, 6/14	A1	(11) International Publication Number: WO 99/47955 (43) International Publication Date: 23 September 1999 (23.09.99)
(21) International Application Number: PCT/US98/14340 (22) International Filing Date: 10 July 1998 (10.07.98) (30) Priority Data: 09/040,090 17 March 1998 (17.03.98) US (71) Applicant: MINNESOTA MINING AND MANUFACTURING COMPANY [US/US]; 3M Center, P.O. Box 33427, Saint Paul, MN 55133-3427 (US). (72) Inventor: MACDOUGALL, Trevor, W.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). (74) Agents: HO, Néstor, F. et al.; Minnesota Mining and Manufacturing Company, Office of Intellectual Property Counsel, P.O. Box 33427, Saint Paul, MN 55133-3427 (US).	(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>	

(54) Title: PASSIVELY COMPENSATED OPTICAL FIBERS



(57) Abstract

A passively compensated optical fiber (20) includes an optical fiber and a support member (5) attached to the optical fiber at a first attachment point (2) and at a second attachment point (4). The distance between the first attachment point and the second attachment point increases with increasing temperature due to expansion of the support member. As temperature changes, support (5) expands, i.e., the distance between first point (2) and second point (4) increases. The expansion creates a strain which is transferred through adhesive (8) to cladding (40), core (30), and LPG (31). The strain transferred to the LPG (31) from the thermally expanding support (5) negates or compensates the central wavelength shift of the long-period grating (31) due to temperature.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

PASSIVELY COMPENSATED OPTICAL FIBERSBackground of the Invention

5 The invention relates to optical fibers and long-period gratings.

Optical fibers are used to guide light which might, typically, be an optical signal used in telecommunications. In general, an optical fiber
10 includes an inner core and an outer clad having an index of refraction less than the inner core. The difference in the index of refraction creates internal reflections forcing the light to propagate along the inner core and preventing it from leaking out of the
15 fiber.

Some optical fibers include long-period gratings (LPG). A long-period grating is formed by producing a series of perturbations in the index of refraction of the inner core. It is well known in the
20 art how to produce optical fibers having long-period gratings, e.g., as described in U.S. Pat. No. 5,430,817. In general, the optical fibers are made from high purity SiO_2 or other optical materials, e.g., germanosilicate. The long-period gratings can be made
25 by first loading the fibers with hydrogen or deuterium and then selectively exposing the core of an optical fiber to ultra-violet light. Typically, the perturbations are formed by exposing the core through the cladding to an intensity pattern that is produced
30 by transmitting an ultra-violet beam directed through an amplitude mask. The spacing of the perturbations creates a grating characterized by a center wavelength at which light will no longer propagate through the

optical fiber. Long-period gratings with different perturbation spacings have different center wavelengths. In general, long-period gratings are those in which the spacing of the perturbations is at least 10 times larger than the wavelength of input light. Typically, the period is in the range 15-1500 μm for center wavelengths between 700 and 1500 nm. In addition, long-period gratings can have a span of perturbations extending for a few cm.

Long-period gratings are used in optical fibers to filter out selected wavelengths from an optical signal, e.g., like a notch filter. As an optical signal propagates through the core and encounters a long-period grating, specific wavelengths of light, i.e., the center wavelength of the grating, are converted from a guided mode of the core to a non-guided mode of the cladding. A guided mode propagates through the core of the optical fiber. A non-guided mode of the cladding dissipates through the cladding and does not propagate through the optical fiber. The center wavelength conversion from a guided mode to a non-guided mode is a function of the perturbation spacing and the difference in the effective index of refraction between the guided and non-guided mode. Typically, for a single mode optical fiber, there is only one core guided mode, but several cladding non-guided modes. In addition, each non-guided mode of cladding is characterized by an unique effective index of refraction. Therefore, for a given perturbation spacing, there are several non-guided cladding modes, and thus, several center wavelengths at which light is converted from a guided mode to non-guided modes. In addition, for a given center wavelength, there are

several perturbation spacings at which light is converted from a guided mode to non-guided mode.

Optical fibers having long-period gratings are useful as amplified spontaneous emission (ASE) filters, erbium-doped fiber amplifier (EDFA) gain equalizers and sensors. The use of optical fibers having long-period gratings continues to increase. Long-period gratings, however, are sensitive to changes in temperature. Typically, a central wavelength of 1550 nm shifts by 2 to 30 nm per 100°C change in temperature. It is important, for instance, in telecommunication applications that the central wavelength of the long-period grating be constant over temperature ranges of 100°C.

15

Summary of the Invention

In general, in one aspect, the invention features a passively compensated optical fiber having an optical fiber and a support member. The support member is attached to the optical fiber at a first attachment point and at a second attachment point. The distance between the first attachment point and the second attachment point increases with increasing temperature due to expansion of the support member.

The passively compensated optical fiber includes a stainless steel, aluminum, or copper support attached with an epoxy to the optical fiber at two points. The epoxy can be ultra-violet curable. The passively compensated optical fiber also includes a coating, an outer core, and an inner core. The inner core includes a long-period grating between the first attachment point and the second attachment point.

In another aspect, the invention features a method of fabricating a passively compensated optical fiber. The method includes identifying the strain response and thermal response for a long-period grating having a central wavelength, choosing a support member having a coefficient of linear expansion which compensates the optical fiber, and attaching the optical fiber to the support member at a first attachment point and at a second attachment point.

10 In another aspect, the invention features a method of fabricating a passively compensated optical fiber. The method includes calculating an optical fiber design for compensating an optical fiber having a center wavelength and a substrate having a coefficient of thermal expansion, manufacturing an optical fiber
15 having a long-period grating fabricated using the calculated optical fiber design, and attaching the fabricated optical fiber to a support member at a first attachment point and at a second attachment point.

20 In another aspect, the invention features a method of compensating an optical fiber. The method includes providing an optical fiber, attaching the optical fiber at a first attachment point and at a second attachment point, and increasing the distance between the first
25 attachment point and the second attachment point in response to an increase in temperature.

Preferably, the method of compensation is done passively.

The invention provides a passively compensated LPG
30 device by attaching an optical fiber having a LPG to a thermally expanding support.

Brief Description of the Drawing

Fig. 1 is a schematic view of a passively compensated long-period grating device;

5 Fig. 2 is a plot of the transmission output signal of a passively compensated long-period grating device at 25°C and 100°C;

Fig. 3 is a plot of the center wavelength verses perturbation spacing for coupling between a guided core
10 mode and several non-guided cladding modes; and

Fig. 4 is a plot of the change in the effective index of refraction per change in the effective index of refraction of SiO₂, versus non-guided cladding mode.

Description of the Preferred Embodiments

Referring to Fig. 1, a passively compensated LPG device 10 includes an optical fiber 20 having a core 30, a cladding 40, and a coating 50 for protecting the
20 optical fiber 20. Core 30 includes a long-period grating 31 having a plurality of refractive index perturbations 32 spaced along the central axis of LPG device 10 for a distance, D. A section 105 of the coating 50 surrounding the long-period grating 31 is
25 removed to expose the cladding 40. The exposed cladding 40 is attached at a first point 2 and at a second point 4 to a support 5 with an adhesive 8.

As the temperature changes, the central wavelength of the LPG 31 shifts, e.g., to longer wavelengths. In
30 LPG device 10, strain applied to the LPG 31 by the thermal expansion of support 5 shifts the central wavelength in the opposite direction, e.g., to shorter wavelengths. Therefore, a shift in the central

wavelength due to temperature can be negated or compensated by applying strain to LPG 31. As temperature changes, support 5 expands, i.e., the distance between first point 2 and second point 4 increases. The expansion creates a strain which is transferred through adhesive 8 to cladding 40, core 30, and LPG 31. The strain transferred to the LPG 31 from the thermally expanding support 5 negates or compensates the central wavelength shift of the long-period grating 31 due to temperature.

The response of the central wavelength to changes in temperature and strain are used to determine the amount of applied strain needed to compensate a shift in the central wavelength. The affect of temperature and strain on the center wavelength is:

$$d\lambda = \frac{d\lambda}{dT} \Delta T + \frac{d\lambda}{d\epsilon} \Delta \epsilon \quad (1)$$

where $d\lambda/dT$ is the change in the central wavelength per change in temperature, referred to as the thermal coefficient, and where $d\lambda/d\epsilon$ is the change in the central wavelength per change in strain, referred to as the strain coefficient. $\Delta \epsilon$ is equal to the strain applied to the grating and ΔT is equal to the temperature change. An optical fiber with a LPG has a positive thermal coefficient. An optical fiber with a LPG can have either a positive or negative strain coefficient. For passive compensation, the optical fiber with a LPG is designed such that the optical

fiber has a negative strain coefficient. The design of the optical fiber will be discussed in further detail below. All of the temperature effects (i.e., the change in the index of refraction of the core and of the cladding as well as thermal expansion of the glass) are included in the temperature coefficient. Similarly, all of the strain effects (i.e., the change in the index of refraction of the core and of the cladding as well as the change in the spacing of the grating) are included in the strain coefficient.

The strain and temperature effects are compensated when there is no change in the center wavelength, i.e., when $d\lambda = 0$. Rearranging Eq. 1, compensation is achieved when

$$\frac{d\lambda}{dT} \Delta T = -\frac{d\lambda}{d\epsilon} \Delta \epsilon$$

(2)

Eq. 2 is rearranged to yield:

$$-\frac{d\lambda/dT}{d\lambda/d\epsilon} = \frac{\Delta \epsilon}{\Delta T} = CTE$$

(3)

The ratio of the thermal coefficient and the strain coefficient is negative because $d\lambda/d\epsilon < 0$. Thus, the left hand side of Eq. 3 is positive and is equal to the ratio of strain applied to the grating, $\Delta \epsilon$, per change in temperature, ΔT . The ratio $\Delta \epsilon/\Delta T$ is also equal to

the coefficient of thermal expansion (CTE) of a material. Therefore, compensation occurs when an optical fiber with an LPG is attached to a support having a CTE equal to the left hand side of Eq. 3.

5 Referring back to Fig. 1, a passively compensated LPG device 10 is manufactured from an optical fiber 20 having a 58 micron thick cladding 30 and a 9 micron thick core 40. The cladding is fabricated from SiO_2 and the core is fabricated from SiO_2 doped with GeO_2 . The
10 effective index of refraction of the core is 1.45 and the effective index of refraction of the cladding is 1.4446. Core 40 includes a LPG 31 having a plurality of refractive index perturbations 32 spaced by, 70.5
15 2.5 cm. A 45mm section 105 of coating 50 surrounding LPG 31 is removed. The thermal and strain coefficients of optical fiber 20 are measured as 0.048 nm/ $^{\circ}\text{C}$ and -0.0028 nm/microstrain. These values are used in Eq. 3 to determine the CTE value needed for compensation.
20 Optical fiber 20 is attached at a first point 2 10 mm from one end of LPG 31 and at a second point 10 mm from the other end of LPG 31. The fiber is attached with a UV curable adhesive 8, e.g., EMCAST 1060A from Electronic Materials, located in Breckenridge,
25 Colorado, to an aluminum support 5 having a CTE of 24 microstrain/ $^{\circ}\text{C}$. Adhesive 8, typically, is attached to the cladding 40 of optical fiber 100 approximately 10 mm from either end of LPG 31.

Referring to Fig. 2, the center wavelength of
30 stabilized LPG device 10 is monitored as the temperature is increased from 25 $^{\circ}\text{C}$ to 100 $^{\circ}\text{C}$. The change in center wavelength per change in temperature is measured as 0.0017 nm/ $^{\circ}\text{C}$. The stabilized LPG device

results in reduction, by a factor of 25, of the center wavelength's sensitivity to temperature changes.

The support is made of any material, e.g., stainless steel, aluminum, or brass, having a CTE which satisfies Eq. 3, for an optical fiber with a LPG having measured coefficients of temperature and strain. The range of CTE values, however, is limited to the CTE values of known support materials. Therefore, a support material having a CTE equal to the ratio of measured thermal and strain coefficients for an optical fiber might not exist. In this case, either the support having the CTE which best satisfies Eq. 3 is used or an optical fiber with a LPG having a different perturbation spacing is manufactured. In general, optical fibers manufactured with smaller perturbation spacing can be compensated by using existing support materials. For example, assume that one optical fiber (Fiber A) with a center wavelength of 1800 nm is fabricated with a perturbation spacing of 100 microns and another optical fiber (Fiber B) with a center wavelength of 1800 nm is fabricated with a perturbation spacing of 300 microns. Of the two fibers, Fiber A is more likely to be compensated by using existing support material than is Fiber B, because Fiber A has a smaller perturbation spacing.

Whether one can compensate an optical fiber having a particular perturbation spacing and center wavelength is calculable. The coefficients of temperature and strain are affected by the design of the optical fiber, e.g., geometry, materials, and perturbation spacing. Compensation as defined in Eq. 3, is also related to the change in the index of refraction of the optical fiber by:

$$CTE = - \frac{\frac{dn_{SiO_2}}{dT} (1 - \frac{dn_{effclad}}{dn_{SiO_2}})}{d\lambda/dL}$$

(4)

5 where n_{SiO_2} is the index of refraction of fused silica, dn_{SiO_2}/dT is 6.7×10^{-6} per $^{\circ}C$, and $d\lambda/dL$ is the change in the center wavelength per change in the perturbation spacing of the LPG. The CTE values of the support materials are known, e.g., stainless steel has a CTE
 10 value of 11 microstrain/ $^{\circ}C$. The two remaining unknown quantities, $dn_{effclad}/dn_{SiO_2}$ and $d\lambda/dL$, are different for each non-guided cladding mode, but they are calculable. In addition, there are several non-guided modes for which a center wavelength is coupled from a guided
 15 mode. Therefore, the non-guided mode having a $dn_{effclad}/dn_{SiO_2}$ and $d\lambda/dL$ which comes closest to satisfying Eq. 4, for a given center wavelength, is chosen.

The quantities $dn_{effclad}/dn_{SiO_2}$ and $d\lambda/dL$ are calculated by
 20 solving an eigenvalue problem which takes into account the geometry of the fiber, the index of refraction of the core, the index of refraction of the cladding, and the index of refraction of bulk SiO_2 . The process of setting up and solving eigenvalue calculations is
 25 similar to the processes described in setting up the equations for fiber optic modeling and in solving eigenvalue problems found in Monerie, IEEE J. Q. Electronics CE-18, p. 535 (1982), and in Snyder and Love, Optical Waveguide Theory.

Referring to Fig. 3, the results of the eigenvalue calculations can be used to generate graphs of the center wavelength versus perturbation spacing. Each solid line in the graph represents coupling between the
5 guided core mode and a single non-guided cladding mode. The non-guided cladding modes are numbered in ascending order from right to left. The results of the eigenvalue calculation also can be used to determine the slope, $d\lambda/dL$, for each non-guided cladding mode.
10 As can be seen from the graph, the lowest non-guided cladding modes have a positive slope, $d\lambda/dL > 0$. Many of the higher non-guided cladding modes, however, have a negative slope. The slope, $d\lambda/dL$, is related to the LPG strain coefficient, $d\lambda/d\epsilon$, by Eq. 5:

15

$$d\lambda/d\epsilon = (d\lambda/dL) L \quad (5)$$

where L is the grating spacing at room temperature, and
20 also represents the change in the perturbation spacing per change in strain. Therefore, the strain coefficient is negative when the slope, $d\lambda/dL$, is negative. Thus, a LPG is designed to have a negative strain coefficient by fabricating the LPG such that the
25 center wavelength coupling occurs between a guided core mode and an higher non-guided cladding mode having a negative slope, $d\lambda/dL < 0$.

In addition to the slope, each non-guided cladding mode also has a $dn_{\text{effclad}}/dn_{\text{SiO}_2}$ value. Referring to Fig.
30 4, results from the eigenvalue problem are used to plot the $dn_{\text{effclad}}/dn_{\text{SiO}_2}$ value versus non-guided cladding mode. Each non-guided cladding mode has a unique set of $d\lambda/dL$

and $dn_{\text{effclad}}/dn_{\text{SiO}_2}$ values. Therefore, for a specific center wavelength, several non-guided cladding mode values are used in Eq. 4 to determine which mode is most effectively compensated.

5 Note that in the embodiments described above, the coating of the optical fiber is removed to transfer strain directly from the thermally expanding support through the cladding and the core to the LPG. A passively compensated LPG device can be made without
10 removing the coating. The optical fiber with coating is attached to a support material. The CTE of the support material needed for passive compensation is calculated by incorporating the strain and thermal responses of the coating into Eq. 3.

15 Although a passively compensated LPG device is described above, an optical fiber having a LPG also can be actively compensated.

Other embodiments are within the scope of the following claims.

What is claimed is:

1. A passively compensated optical fiber device (10) comprising:
 - an optical fiber (20); and
 - 5 a support member (5) attached to the optical fiber at a first attachment point (2) and at a second attachment point (4), wherein the distance between the first attachment point and the second attachment point increases with increasing temperature due to expansion
 - 10 of the support member.
2. The passively compensated optical fiber of claim 1, wherein the support is stainless steel.
- 15 3. The passively compensated optical fiber of claim 1, wherein the support is aluminum.
4. The passively compensated optical fiber of claim 1, wherein the support is copper.
- 20 5. The passively compensated optical fiber of any of claims 1 to 4, wherein the support is attached to the optical fiber at two points with an epoxy.
- 25 6. The passively compensated optical fiber of any of claims 1 to 5, wherein the epoxy is ultra-violet curable.
7. The passively compensated optical fiber of
30 any of claims 1 to 6, wherein the optical fiber includes a coating (50).

8. The passively compensated optical fiber of any of claims 1 to 7, wherein the optical fiber includes an outer cladding (40) and an inner core (30) having a long-period grating (31).

5

9. The passively compensated optical fiber of claim 8, wherein the long-period grating is between the first attachment point and the second attachment point.

10

10. A method of fabricating a passively compensated optical fiber comprising:

identifying the strain response and thermal response for a long-period grating having a central wavelength,

15

choosing a support member having a coefficient of linear expansion which compensates the optical fiber,

20

attaching the optical fiber to the support member at a first attachment point and at a second attachment point.

11. A method of fabricating a passively compensated optical fiber comprising:

25

calculating an optical fiber design for compensating an optical fiber having a center wavelength and a substrate having a coefficient of thermal expansion,

30

manufacturing an optical fiber having a long-period grating fabricated using the calculated optical fiber design,

attaching the fabricated optical fiber to a support member at a first attachment point and at a second attachment point.

- 5 12. A method of compensating an optical fiber comprising:

 providing an optical fiber,
 attaching the optical fiber at a first
10 attachment point and at a second attachment point, and
 increasing the distance between the first
attachment point and the second attachment point in
response to an increase in temperature.

- 15 13. The method of claim 12, wherein the compensation is done passively.




Fig. 1




Fig. 2




Fig. 3




Fig. 4

INTERNATIONAL SEARCH REPORT

International Application No.
PCT/US 98/14340

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 G02B6/293 G02B6/34 G02B6/14

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 G02B H01S

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 042 898 A (MOREY WILLIAM W ET AL) 27 August 1991 see the whole document	1-3, 8-10,12, 13
A	WO 97 28480 A (CORNING INC) 7 August 1997 see page 1, line 24 - line 25 see page 2, line 1 - line 31 see page 3, line 1 - line 16 see page 9, line 28 - line 31 see page 10, line 1 - line 31 see page 11, line 1 - line 31 see figures 1-4	1,5,6, 8-10,12, 13

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *Z* document member of the same patent family

Date of the actual completion of the international search

23 November 1998

Date of mailing of the international search report

18.02.99

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

MATHYSSEK K.

INTERNATIONAL SEARCH REPORT

International Application No.
PCT/JS 98/14340

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>YOFFE G W ET AL: "TEMPERATURE-COMPENSATED OPTICAL-FIBER BRAGG GRATINGS" OPTICAL FIBER COMMUNICATION. SUMMARIES OF PAPERS PRESENTED AT THE CONFERENCE OFC '95, SAN DIEGO, FEB. 26 - MAR. 3, 1995, February 1995, page 134/135 XP000613097 INSTITUTE OF ELECTRICAL AND ELECTRONICS ENGINEERS see the whole document -----</p>	<p>1-3,5, 10,12,13</p>
A	<p>US 5 703 978 A (DIGIOVANNI DAVID JOHN ET AL) 30 December 1997 see claims; figure 1 -----</p>	<p>1,7,8, 10,12</p>

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US 98/14340

Box I Observations where certain claims were found unsearchable (Continuation of Item 1 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:

2. ☐ Claims Nos.:
because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:

3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box II Observations where unity of invention is lacking (Continuation of Item 2 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

1. CLAIMS : 1-10, 12, 13
2. CLAIMS : 11

FOR FURTHER INFORMATION PLEASE SEE FORM PCT/ISA 206 MAILED 09.12.98

1. ☐ As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.

2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.

3. ☐ As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:

4. ☒ No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

1-10, 12, 13

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
- ☒ No protest accompanied the payment of additional search fees.

INTERNATIONAL SEARCH REPORT

International Application No. PCT/US 98/14340

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

1. Claims: 1-10,12,13

refer to a device und the corresponding method of passively compensating it comprising the steps of

- identifying the strain response and thermal response for long-period grating having a central wavelength
- choosing a support member having a coefficient of thermal expansion to compensate the optical fiber and
- attaching the fiber to the support at first and second attachment point.

2. Claim : 11

is directed to a method of passively compensating optical fiber comprising the steps

- calculating an optical fiber design for compensating a fiber having long-period grating with a central wavelength
- manufacturing the grating using the calculated fiber design and
- attaching the fiber to the support at first and second attachment point.

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/JS 98/14340

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5042898 A	27-08-1991	DE 69020167 D	20-07-1995
		DE 69020167 T	26-10-1995
		EP 0507877 A	14-10-1992
		WO 9110151 A	11-07-1991

WO 9728480 A	07-08-1997	AU 2990397 A	22-08-1997
		AU 6897396 A	11-08-1997
		CA 2242676 A	24-07-1997
		CA 2243200 A	07-08-1997
		EP 0875012 A	04-11-1998
		EP 0880718 A	02-12-1998
		WO 9726572 A	24-07-1997

US 5703978 A	30-12-1997	EP 0767391 A	09-04-1997
		JP 9145941 A	06-06-1997
